



UK 1366 B10 / UK 5452

August 2012

PRODUCT DESCRIPTION

UK 1366 B10 / UK 5452 provides the following product characteristics:-

Technology	Polyurethane
Product Type	Structural Adhesive
Cure	Room temperature cure after mixing
Condition	Solvent-free
Components	Two-component
Application	Bonding
Appearance (Comp. A)	Beige
Appearance (Comp. B)	green
Mixing Ratio, by weight Comp. A : Comp. B	4.7 : 1
Mixing Ratio, by volume Comp. A : Comp. B	4 : 1
Product Benefits	<ul style="list-style-type: none"> • Flexible • High Impact Resistance • Good moisture resistance

UK 1366 B10 / UK 5452 is a highly flexible structural bonder that has good adhesion to a variety of metals and plastics and exhibits excellent moisture resistance and impact resistance. Typical application is as a structural bonder for metal and plastics.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A:

Specific Gravity @ 22 °C	1.46
Viscosity @ 25°C, mPa·s (cP) Cone & Plate Rheometer, Cone CP50-1 @ shear rate 50 s ⁻¹	21,600

Flash Point - See MSDS

Part B:

Specific Gravity @ 22 °C	1.27
Viscosity @ 25°C, mPa·s (cP) Cone & Plate Rheometer, Cone CP50-1 @ shear rate 50 s ⁻¹	12,290

Flash Point - See MSDS

Mixed:

Specific Gravity, g/cm ³	1.42
Viscosity @ 25°C, mPa·s (cP) Cone & Plate Rheometer, Cone CP50-1 @ shear rate 50 s ⁻¹	33,760

TYPICAL CURING PERFORMANCE

Fixture Time

Fixture Time, ISO 4587, minutes: Grit Blasted Mild Steel 0.005 mm gap	35
--	----

Curing Properties


Working time bead size = ~10mm (0.4in) by 200mm (8in)	
Working Time on Steel, minutes	30
Working Time on Aluminium, minutes	30
Working Time on Polyethylene, minutes	30

Peak Exotherm Temperature

Peak Temperature Time, 20 gram mass, minutes	14
Peak Exotherm Temperature, 20 gram mass, °C	48

Cure Speed vs. Temperature

The graph below shows the shear strength developed with time at different temperatures on grit blasted aluminum lap shears and tested according to ISO 4587.



TYPICAL PROPERTIES OF CURED MATERIAL

After 7 days @ 22 °C

Physical Properties:

Shore Hardness, ISO 868		55
Compressive Strength, ISO 604	MPa	46
	(psi)	(6,670)
Tensile Strength, ISO 527-3	MPa	10
	(psi)	(1,450)
Tensile Modulus, ISO 527-3	MPa	114
	(psi)	(16,500)
Elongation, at break, ISO 527-3, %		58

TYPICAL PERFORMANCE OF CURED MATERIAL

After 7 days @ 22 °C

Shear Strength

Lap Shear Strength, ISO 4587:

Aluminum	MPa	11.9
	(psi)	(1,725)
Stainless Steel	MPa	8.5
	(psi)	(1,230)
Galvanized Steel	MPa	3.5
	(psi)	(510)
Polycarbonate	MPa	8.9
	(psi)	(1,290)
ABS	MPa	5.5
	(psi)	(800)
PVC	MPa	10.3
	(psi)	(1,495)
Epoxyglass	MPa	9.4
	(psi)	(1,365)
Wood (Mahogany)	MPa	9.1
	(psi)	(1,320)

"T" Peel Strength, ISO 11339:

Aluminum (Gritblasted)	N/mm	4.1
	(lb/in)	(23)


After 3 days @ 22 °C

Impact Strength, ISO 9653, J:


Aluminum (Gritblasted)	40
------------------------	----

Hot Strength

Cured for 7 days @ 22 °C, on stainless steel

**Heat Aging**

Cured for 7 days @ 22 °C, on stainless steel

**Chemical/Solvent Resistance**

Shear Strength on Stainless steel Lapshears, Aged under conditions indicated and tested @ 22 °C

Environment	°C	% of initial strength			
		100 h	500 h	1000 h	3000 h
Water	22	150	95	70	30
Water	60	40	25	35	15
98% RH	40	110	30	35	20
Isopropanol	22	85	110	60	15
Acetic Acid, 10%	22	90	120	70	10
Sodium hydroxide, 4%	22	110	110	60	55
Motor oil (5W40)	22	115	120	120	120

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use:

1. For high strength structural bonds, remove surface contaminants such as paint, oxide films, oils, dust, mold release agents and all other surface contaminants.
2. Use gloves to minimize skin contact. DO NOT use solvents for cleaning hands.
3. **Dual Cartridges:** To use simply insert the cartridge into the application gun and start the plunger into the cylinders using light pressure on the trigger. Next, remove the cartridge cap and expel a small amount of adhesive to be sure both sides are flowing evenly and freely. If automatic mixing of resin and hardener is desired, attach the mixing nozzle to the end of the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of the adhesive and mix thoroughly. Mix for approximately 15 seconds after uniform color is obtained. **Bulk Containers:** Utilize volumetric dispense system to ensure proper mix ratio and utilize mix nozzle to obtain adequate

- mixing.
4. For maximum bond strength apply adhesive evenly to both surfaces to be joined.
 5. Application to the substrates should be made within 8 to 10 minutes. Larger quantities and/or higher temperatures will reduce this working time.
 6. Join the adhesive coated surfaces and allow to cure at 25 °C (77 °F) for 24 hours for high strength. Heat up to 60 °C (140°F), will speed curing.
 7. Keep parts from moving during cure. Contact pressure is necessary.
 8. Excessive uncured adhesive can be cleaned up with ketone type solvents.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 20°C ± 5°C. Storage below 15°C or greater than 25 °C can adversely affect product properties. Component B is frost sensitive. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 µm / 25.4 = mil
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a**

particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0