

# TEROSON EP 5065

June 2014

**Important: This is an experimental product and the relevant Technical Data may change.**

## PRODUCT DESCRIPTION

<b>Technology</b>	Epoxy Resin / Amine
<b>Additional Information</b>	structural bonding material 2-component solvent free impact-resistant

TEROSON EP 5065 is a solvent free, two component adhesive, based on Epoxy resins. It has high initial strength both at high and low temperatures (-40°C - 80°C). Curing can be obtained with both low and high temperature. The cured adhesive film is hard, but not brittle.

## APPLICATION AREAS

TEROSON EP 5065 is mainly used in car repair for structural bonding of metals when requirements in terms of crash behaviors are high (e.g., car body steel with or without e-coat, galvanized steel and aluminum). Coated surfaces are protected against corrosion. Curing can take place at low temperatures or be accelerated using an IR radiator. The assembly bonded shall be designed so that the bonded surface or seams are only subjected to tensile or shear forces, but not to peel forces. It is recommended that bonding should be done with single overlaps. Uncured adhesive can be spot-welded.

## TECHNICAL DATA

(Typical Test Results)

### PART A

Base	Epoxy Resin
Colour	black
Density	approx. 1.1 g/ml
Viscosity	approx. 23 Pa.s
Measuring equipment	Physika UDS 200
Measuring system	plate/plate Ø 20 mm
Cross head peel speed	10 s <sup>-1</sup>
Temperature	23 °C

### PART B

Base	Amine
Colour	grey-green
Density	approx. 1.0 g/ml
Viscosity	approx. 2 Pa.s
Mixing ratio A:B	200 : 100

### Mixture (PART A+B)

Colour	black
Odour	almost without odour
Pot life (23°C, 50% rh)	approx. 60 min(s)

Initial strength	after 8 hours (23°C, 50% rh) after approx. 15 minutes (80 °C object temperature)
Curing times final strength	approx. 2 d at 23 °C or 30 minutes at 80 °C object temperature
Shear strength (based on DIN EN 1465) Steel, 0.2 mm thick layer (7 d at 23 °C, 50 % rh) at 23 °C	25 MPa
Peel test (DIN EN ISO 11339) Steel, 0.2 mm thick layer (7 d at 23 °C, 50 % rh)	6 N/mm <sup>2</sup>
E-Modulus	>1,500 MPa

## PRELIMINARY STATEMENT

Prior to application it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

## PRETREATMENT

The substrate should be dry, free from dust, oil, grease and other contaminants. An improvement of the adhesion can be achieved by grindings or sandblasting of the surface.

## APPLICATION

TEROSON EP 5065 is processed from a 2:1 cartridge. Prior to screwing the static mixer, a small amount of the material should be pressed out to ensure that both components are passed on simultaneously. Now, the static mixer is screwed onto it. To ensure proper mixing, discard the first approx. 4 cm of the adhesive bead. Only use cartridge pistols that are equipped with a piston rod. After mixing, the adhesive is ready for use and must be processed within 1 hour, since viscosity increases when curing starts. The processing time depends on the temperature. In order to avoid the bonded parts being displaced, it is recommended that they should always be fixed.

# TEROSON EP 5065

June 2014

## CURING

The bonded parts, which have been fixed by means of a slight pressure applied to them, can be cured at room temperature or higher.

They can be painted over after having reached their initial strength.

If suitable equipment for curing at higher temperature (infrared radiator, paint cabin that can be heated to 40 – 80 °C or other equipment) is available, this should always be given preference over curing at room temperature for the following reasons:

- Shorter curing time; further processing or treatment is possible after only 2 hours approx.
- Higher strength is achieved
- Higher resistance of the adhesive bond against chemical loads

## CLEANING

Fresh, uncured material can be removed with TEROSON VR 20. Cured adhesive can only be removed mechanically.

## STORAGE

Frost sensitive	under certain conditions (may cristalize, reversible at 60 °C)
Recommended storage temperature	15 to 25 °C
Shelf life	12 months in original packaging

## Disclaimer

### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out

your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

### Henkel AG & Co. KGaA

D-40191 Düsseldorf, Germany  
Phone: +49-211-797-0  
www.henkel.com

### Henkel Central Eastern Europe GmbH

A-1030 Wien, Austria  
Phone: +43-1711-040  
www.henkel.com

### Henkel & Cie AG

CH-4133 Pratteln, Switzerland  
Phone: +41-61-825-7000  
www.henkel.com

